

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-354949

(43)Date of publication of application : 25.12.2001

(51)Int. CI.

C09K 3/10
C03C 27/06
// C08L 51/06

(21)Application number : 2000-175214 (71)Applicant : YOKOHAMA RUBBER CO LTD:THE

(22)Date of filing : 12.06.2000 (72)Inventor : TAKEYAMA SHUICHI
IGAWA KATSUHIRO
WATANABE JIRO

(54) SEALING AGENT COMPOSITION AND DOUBLE GLAZING USING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a sealing material composition which does not need a metal spacer or a secondary sealing material in preparing a double glazing, does not need the use of a primer or an adhesive resin, and is especially useful as a sealing material, and to provide a double glazing the production process of which is greatly simplified because of the use of the composition as a sealing material. SOLUTION: This sealing material composition comprises a continuous phase formed from a non-crystalline polyolefin to which a silane compound having hydrolyzable silyl groups has been grafted and a disperse phase formed from a thermoplastic resin and/or an elastomer and has a moisture permeability of 200 g/m².24h or lower (30 μm thickness).

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision
of rejection]

[Kind of final disposal of application
other than the examiner's decision of
rejection or application converted
registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

12/7/2005

Copyright (C); 1998, 2003 Japan Patent Office

12/7/2005